



SAS SEALTRON® 1026

Nickel Graphite filled Silicone

Elastomer			Silicone
Particle			Nickel Coated Graphite
O	ture (°C)	Max	160
Operating Tempera		Min	-55
Specific Gravity (+/- 13%)			1.95
Hardness Shore A(+/- 7)			60
Compression Set (70 hrs at 100°C,% Max)			30
Tensile Strength (psi, Min)			200
Tear Strength (lb/in., Min)			50
Elongation % Min Max		100	
		Max	-
Volume Resistivity (ohm-cm, Max)			0.1
Shielding Effectiveness (minimum)	200 KHz (H Field)		NOT TESTED
	20 MHz (E Field)		100
	100 MHz (E Field)		100
	500 MHz (E Field)		100
	1 GHz (Plane Wave)		100
	10 GHz (Plane Wave)		100
	40 GHz (Plane Wave)		NOT TESTED

SAS Industries, Inc. REACH / RoHS Compliance : SAS does not use or store any metallic mercury, mercury compounds or mercury containing products at our

facility and that all products listed herein are RoHS Compliant 2011/65/EU. SAS also certifies that all of our products do not contain any of the REACH Substances

of Very High Concern (SVHC) as published by ECHA (European Chemical Agency).

Features and Benefits

Moderate Electrical Conductivity **Excellent Mechanicals** Good Galvanic Compatibility

SAS SEALTRON® 1026 is an excellent conductive elastomer choice in situations requiring shielding effectiveness, environmental sealing, reliability

SAS SEALTRON® 1026 is a combination of Nickel Coated Graphite and Silicone, combined to create a conductive matrix.

SAS SEALTRON® 1026 is available in many different variations including:

- Molded Parts
- Die Cut/Water Jet Cut Parts
- **Extrusions**
- Sheets
- Co-Molded Parts
- Co-Extrusions

Postal Address: SAS Industries Inc. PO Box 245 Manorville, NY 11949 Physical Address: SAS Industries Inc. 939 Wading River Manor Rd. 100 Corporate Drive Manorville, NY 11949

Physical Address: SAS Industries, Inc. Elizabeth City, NC 27909

Telephone: 631.727.1441 Fax: 631.727.1387

E-mail: info@sasindustries.com sales@sasindustries.com