



SAS SEALTRON® 1034

Features and Benefits

Good Electrical Conductivity **Excellent Mechanicals** Good Shielding Performance

SAS SEALTRON® 1034 is an excellent conductive elastomer choice in situations requiring shielding effectiveness, environmental sealing, reliability

SAS SEALTRON® 1034 is a combination of Silver Plated Glass and Silicone. combined to create a conductive matrix.

SAS SEALTRON® 1034 is available in many different variations including:

- Molded Parts
- Die Cut/Water Jet Cut Parts
- **Extrusions**
- Sheets
- Co-Molded Parts
- Co-Extrusions

Silver Plated Glass filled Silicone

Elastomer			Silicone
Particle		Silver Plated Glass	
Operating Tampers	ture (°C)	Max	160
Operating Tempera		Min	-55
Specific Gravity (+/- 13%)			1.8
Hardness Shore A(+/- 7)			47
Compression Set (70 hrs at 100°C,% Max)			30
Tensile Strength (psi, Min)			100
Tear Strength (lb/in., Min)			35
Elongation %		Min	120
		Max	-
Volume Resistivity (ohm-cm, Max)			0.01
Shielding Effectiveness (minimum)	200 KHz (H Field)		NOT TESTED
	20 MHz (E Field)		50
	100 MHz (E Field)		100
	500 MHz (E Field)		90
	1 GHz (Plane Wave)		80
	10 GHz (Plane Wave)		75
	40 GHz (Plane Wave)		NOT TESTED

SAS Industries, Inc. REACH / RoHS Compliance : SAS does not use or store any metallic mercury, mercury compounds or mercury containing products at our

facility and that all products listed herein are RoHS Compliant 2011/65/EU. SAS also certifies that all of our products do not contain any of the REACH Substances

of Very High Concern (SVHC) as published by ECHA (European Chemical Agency).

Postal Address: SAS Industries Inc. PO Box 245

Manorville, NY 11949

Physical Address: SAS Industries Inc. 939 Wading River Manor Rd. 100 Corporate Drive Manorville, NY 11949

Physical Address: SAS Industries, Inc. Elizabeth City, NC 27909

Telephone: 631.727.1441 Fax: 631.727.1387

E-mail: info@sasindustries.com sales@sasindustries.com