

SAS SEALTRON® 1066

Features and Benefits

Excellent Electrical Conductivity
 Excellent Mechanicals
 Excellent Shielding Performance

SAS SEALTRON® 1066 is an excellent conductive elastomer choice in situations requiring shielding effectiveness, environmental sealing, reliability

SAS SEALTRON® 1066 is a combination of Silver Plated Copper and Silicone, combined to create a conductive matrix.

SAS SEALTRON® 1066 is available in many different variations including:

- Molded Parts
- Die Cut/Water Jet Cut Parts
- Extrusions
- Sheets
- Co-Molded Parts
- Co-Extrusions

Silver Plated Copper filled Silicone

Elastomer		Silicone
Mil-DTL-83528 Type		A
Particle		Silver Plated Copper
Operating Temperature (°C)	Max	125
	Min	-55
Specific Gravity (+/- 13%)		3.5
Hardness Shore A (+/- 7)		65
Compression Set (70 hrs at 100°C, % Max)		32
Tensile Strength (psi, Min)		200
Tear Strength (lb/in., Min)		35
Elongation %	Min	100
	Max	300
Volume Resistivity (ohm-cm, Max)		0.004
Shielding Effectiveness, dB, (as tested)	200 KHz (H Field)	110
	20 MHz (E Field)	113
	100 MHz (E Field)	147
	500 MHz (E Field)	140
	1 GHz (Plane Wave)	147
	10 GHz (Plane Wave)	137
	40 GHz (Plane Wave)	110

SAS Industries, Inc. REACH / RoHS Compliance : SAS does not use or store any metallic mercury, mercury compounds or mercury containing products at our facility and that all products listed herein are RoHS Compliant 2015/863/EU. SAS also certifies that all of our products do not contain any of the REACH Substances of Very High Concern (SVHC) as published by ECHA (European Chemical Agency).

Postal Address:
 SAS Industries Inc.
 PO Box 245
 Manorville, NY 11949

Physical Address:
 SAS Industries Inc.
 939 Wading River Manor Rd.
 Manorville, NY 11949

Physical Address:
 SAS Industries, Inc.
 100 Corporate Drive
 Elizabeth City, NC 27909

Telephone: 631.727.1441
 Fax: 631.727.1387
 E-mail: info@sasindustries.com
 sales@sasindustries.com

NOTICE: SAS Industries, Inc. does not assume any responsibility or liability for any advice furnished by it, or for the performance or results of any installation or use of the product(s) or of any final product into which the product(s) may be incorporated by the purchaser and/or user. The purchaser and/or user should perform its own tests to determine the suitability and fitness of the product(s) for the particular purpose desired in any given situation.